PHOSBRAZ M70

Copper Phosphorous Brazing Alloy

TECHNICAL DATA SHEET 65

Specifications:

Alloy	Working Temperature (˚C)	NF EN ISO 17672	AWS A-5.8	DIN 8513
Cu-P	730	CuP 180	B Cu-P2	L-Cu P7

Characteristics:

PHOSBRAZ M70 Alloy with higher fluidity, specially made for strong brazing of fitting, pipes and Fit up, with average joint gaps. Its higher Phosphorus content makes it more fluid. Alloy with self-fluxing properties. The corrosion resistance this alloy is comparable to that of copper excepts when the joint is exposed to sulphuric containing gas or at elevated temperatures as in a cooking range. Under these conditions, it is expected that, this alloy will undergo progressive deterioration as other copper phosphorus alloy with Silver or without silver.

Applications:

PHOSBRAZ M70 joining copper to copper it is act as self-fluxing alloy and does not required additional flux. It can be used on cuprous alloys (bronze, brass) with Phosbraz flux, electrical industry, Plumbing trade. This brazing alloy is not recommended to be used for the media having sulphur. Also it is not allowed to use for joining steels (Fe) or materials containing Iron(Fe), Nickel (Ni), Cobalt (Co) as it will form brittle phase in the joint. In Air conditioning and refrigeration application, **PHOSBRAZ M70** can be used for the service temperature between +150˚C (without loss in strength) upto -20˚C. This alloy can be used for flame…Maximum short service joint operating temperature 200˚C.

Typical Chemical Compositions (%):

Cu	P	Al	Bi	Cd	Pb	Zn	Zn + Cd	Max. impurities
Reminder	7.00	<0.01	<0.030	<0.01	<0.025	<0.050	<0.05	<0.25

Typical Physical Properties:

Colour	Solidus (˚C)	Liquidus (˚C)	Density g/cm³	Elongation %	Tensile strength (MPa)	Electrical Conductivity (%IACS)	Electrical Resistivity (Micro-ohom-cm)
Copper	710	805	8.0	4%	450	7.48	23.05

Properties of Brazed Joint:

The properties of a brazed joint dependent upon numerous factors including base metal properties, joint design, metallurgical interactions between the base metal and the filler metal.

Standard Size and Types & Heating Source Recommendation:

Size (mm)	Type				OXY/ACETYLÈNE	INDUCTION	AÉRO-PROPANE	FOUR/OVEN
	Bare	Coated	Coil	Preforms				
1.50 ,2.00,2.50,3.00	√	–	–	–	√	√	**X**	**X**

Preform sizes and other type other than above standard dimensions are solicited case to case basis

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com – info@fsh-welding.fr

Rev 09/2016